



Material & Engineering Laboratory-Taichung

# TEST REPORT



REPORT NO. TV-14-02951XA  
PAGE NO. 1 OF 2  
DATE Sep. 25, 2014

Applicant	HO YU TECHNOLOGY CO., LTD.
Address	No.31, Ln.295, Sec.3, Hanxi W.Rd. Beitun Dist., Taichuag City, Taiwan(R.O.C)
Product Description	VQ-800, Concrete Nano Sealer And Hardener
Product Type	VQ-800
Product Color	Transparent Liquid
Manufacturer	HO YU TECHNOLOGY CO., LTD.
Product Submitted By	HO YU TECHNOLOGY CO., LTD.
Received Date	Sep. 19, 2014
Tested Date	Sep. 19, 2014~Sep. 25, 2014
Remark	The information mentioned in the above section is provided by Client (Exclude Date of Sample Received and Date of Testing)

Test Request :

Friction test

Test Method :

Friction test -ASTM D1894-14  
Static and Kinetic Coefficients of Friction of Plastic Film and Sheeting (C-Type)

Test Result :

- PLEASE SEE ATTACHED SHEETS -  
- - -1- - -

The required specification(s) offered in this test report is/are for reference only.  
The conformity judgment is at the Applicant's final verdict.

Signed for and on behalf of  
SGS TAIWAN Ltd.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

## TEST REPORT



REPORT NO. TV-14-02951XA

PAGE NO. 2 OF 2

DATE Sep. 25, 2014

Test Apparatus :

Name	Brand	Model
Tensile Machine	INSTRON	3369

Test Result :

Test Item	Result	
Friction test	Dry	0.60 (s=0.051)
	Wet	0.65 (s=0.081)

Note : 1. Test rate : 150±30 mm/min


2. Touch surface-rubber(Hardness Shore A55±5)

3. Samples+ mass load : 229.68g


4. 「s」 = standard deviation

5. This Test Report is an additional original report of TV-14-02951X. Issued date : Sep. 25, 2014.

Test Photo :



Touch surface



Testing

---oOo---

The required specification(s) offered in this test report is/are for reference only.  
The conformity judgment is at the Applicant's final verdict.

Signed for and on behalf of  
SGS TAIWAN Ltd.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.