

Material & Engineering Laboratory-Kaohsiung

Test Report

Report No. : KB-18-03156A

C-18-06764

Page No.

OF

Date of Report: Apr. 20, 2018

Applicant

HONG YUAN LIN TECHNOLOGY CO., LTD.

Supplier

HONG YUAN LIN TECHNOLOGY CO., LTD.

Sample Name

VQ-800 Concrete Nano Sealer and Densifier

Other Information

Product type: VQ-800

Sample Submitted By

HONG YUAN LIN TECHNOLOGY CO., LTD.(YEH, YAO-CHENG)

Date of Sample Received Apr. 09, 2018

Date of Testing

Apr. 09, 2018~Apr. 20, 2018

Remark

The information mentioned in the above section is provided

by Client(Exclude Date of Sample Received and Date of Testing)

Test Result:

Test Items	Test Method	Test Result
Taber Abrasion (g) Control g	group Poforto CNE 10785(1084)	9.9131
(AA-180, 5000cycles, 500 g) Test grou	Refer to CNS 10785(1984)	0.6474

Note. 1. Test by SGS Kaohsiung Polymer Laboratory(Report NO.KV-18-03118A)

2. This Test Report is an additional original report of KB-18-03156 C-18-06764.

Issued date: Apr. 20, 2018.

---- 000 ----

The required specification(s) offered in this test report is/are for reference only. The conformity judgment is at the Applicant's final verdict.

Signed for and on behalf of SGS Taiwan Ltd.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

TWO 3.756662 TWC 3756662

SGS Taiwan Ltd. No.61, Kai -Fa Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan /高雄市楠梓加工出口區開發路61號 技股份有限公司 t(886-7) 301-2121 f(886-7) 301-1165 www.sgs.tw