

材料及工程實驗室-台中

試驗報告

報告編號:TV-14-02951X-1

數: 1 OF 2 頁

報告日期:103年09月25日

位: 泓垣霖科技有限公司 委

址:臺中市北屯區旱溪西路3段295巷31號 地

稱: VQ-800 混凝土矽晶密封固化劑 產 品 名

產 型 號: VQ-800 品

色:透明液體 產 品 顏

製 造 商: 泓垣霖科技有限公司 廠

送 驗 廠 商: 泓垣霖科技有限公司

期: 103年 09月 19日 件 收 日

期: 103年 09月 19日~103年 09月 25日 試

註: 1. 以上資料由顧客提供(收件及試驗日期除外) 備

> 2. 除非另有說明, 此報告結果僅對測試之樣品負責 未經本公司事先書面同意,此報告不可部分複製

試驗要求:

摩擦係數

試驗方法:

摩擦係數-ASTM D1894-14

Static and Kinetic Coefficients of Friction of Plastic Film and Sheeting (C-Type)

試驗結果:

本報告若有提供規範值時,該規範值僅供參考,合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

台灣檢驗科技股份有限公司

No. 9, 14th Rd. Taichung Industrial Park, Taichung 40755, Taiwan /40755 台中市台中工業區14路9號 t (886-4) 2359-1515 f (886-4) 2359-2557 www.sgs.tw



材料及工程實驗室-台中

試驗報告

報告編號:TV-14-02951X-1

數: 2 OF 2 頁

報告日期:103年09月25日

試驗設備:

儀器名稱 型號 廠牌 拉伸試驗機 **INSTRON** 3369

試驗結果:

試驗項目		結果
摩擦係數	乾式	0.60 (s=0.051)
	濕式	0.65 (s=0.081)

註:1. 試驗速率:150±30 mm/min

2. 摩擦介面: 橡膠(Shore Type A 55)

3. 砝碼+試樣重量: 229.68g

4. 「s」係為標準差

本試驗報告取代TV-14-02951X,原試驗報告作廢,報告修改日期104年07月03日

試驗照片:



試樣狀態



試驗狀態

- - -oOo- - -

本報告若有提供規範值時,該規範值僅供參考,合格之判定以委託單位實際要求為準。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

TWB 5482498