



Material and Engineering Laboratory-Taichung

# TEST REPORT



REPORT NO. TV-18-02930A  
 PAGE NO. 1 OF 2  
 DATE Jul. 30, 2018

Applicant HONG YUAN LIN TECHNOLOGY CO., LTD.  
 Product Description WATER-BASED CONCRETE WATERPROOF SEALER  
 Product Type VQ-1009  
 Product Color White Emulsion  
 Manufacturer HONG YUAN LIN TECHNOLOGY CO., LTD.  
 Supplier HONG YUAN LIN TECHNOLOGY CO., LTD.  
 Received Date May 10, 2018  
 Tested Date May 10, 2018~May 25, 2018  
 Remark The information mentioned in the above section is provided by Client  
 (Exclude Date of Sample Received and Date of Testing)

Test Request :

Friction test

Test Method :


Friction test -ASTM D1894-14  
 Static and Kinetic Coefficients of Friction of Plastic Film and Sheeting (C-Type)

Test Result :

- PLEASE SEE ATTACHED SHEETS -

---1---

The required specification(s) offered in this test report is/are for reference only.  
 The conformity judgment is at the Applicant's final verdict.



Signed for and on behalf of  
 SGS TAIWAN Ltd.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

## TEST REPORT



REPORT NO. TV-18-02930A  
 PAGE NO. 2 OF 2  
 DATE Jul. 30, 2018

Test Apparatus :


| Name            | Brand   | Model |
|-----------------|---------|-------|
| Tensile Machine | INSTRON | 3369  |

Test Result :

| Test Item           | Result         |
|---------------------|----------------|
| Friction test - Wet | 0.52 (s=0.031) |

- Note :
1. Test rate : 150±30 mm/min
  2. Touch surface : Rubber( Shore Type A 60±5)
  3. Samples + Mass load : 228.45
  4. 「s」 = standard deviation
  5. This Test Report is an additional original report of TV-18-02930 Issued date : Jul. 30, 2018

Test Photo :



---oOo---

The required specification(s) offered in this test report is/are for reference only.  
 The conformity judgment is at the Applicant's final verdict.

*[Signature]*  
 Signed for and on behalf of  
 SGS TAIWAN Ltd.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.