

試驗報告



報告編號：TV-18-02930

頁數：1 OF 2

報告日期：107年07月30日

委託單位：泓垣霖科技有限公司
產品名稱：水性混凝土防水密封劑
產品型號：VQ-1009
產品顏色：白色乳液
製造廠商：泓垣霖科技有限公司
供應廠商：泓垣霖科技有限公司
收件日期：107年05月10日
試驗日期：107年05月10日~107年05月25日
備註：1. 以上資料由顧客提供(收件及試驗日期除外)
2. 除非另有說明，此報告結果僅對測試之樣品負責
未經本公司事先書面同意，此報告不可部分複製

試驗要求：

摩擦係數

試驗方法：

摩擦係數-ASTM D1894-14
Static and Kinetic Coefficients of Friction of Plastic Film and Sheeting (C-Type)

試驗結果：

- 請詳附件 -

---1---

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準。

報告簽署人

試驗報告



報告編號：TV-18-02930

頁數：2 OF 2

報告日期：107年07月30日

試驗設備：


儀器名稱	廠牌	型號
拉伸試驗機	INSTRON	3369

試驗結果：

試驗項目	結果
摩擦係數-濕式	0.52 (s=0.031)

- 註：1. 試驗速率：150±30 mm/min
 2. 摩擦介面：橡膠(Shore Type A 60±5)
 3. 砝碼+試樣重量：228.45g
 4. 「s」係為標準差

試驗照片：



---oOo---

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準。

(Handwritten signature)
 報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.