



材料及工程實驗室-台中

試驗報告

報告編號:TV-16-02345Z 數: 1 OF

報告日期:105年07月07日

委 託 單 位: 泓垣霖科技有限公司

址: 406 臺中市北屯區旱溪西路三段 295 巷 31 號 地

稱: 高硬度矽晶奈米漆 產 品 名

號: VQ-3200 刑 產 產 品 色: 無色透明 顏

日

製 诰 商: 泓垣霖科技有限公司 廠 供 商: 泓垣霖科技有限公司 應 廠 送 驗 商: 泓垣霖科技有限公司 廠 期: 105年 06月 27日 收 件

試 期: 105 年 06 月 27 日~105 年 07 月 07 日 驗 H

註: 1. 以上資料由顧客提供(收件及試驗日期除外) 備

> 2. 除非另有說明,此報告結果僅對測試之樣品負責 未經本公司事先書面同意,此報告不可部分複製

試驗要求:

鉛筆硬度

試驗方法:

CNS 10757(1995) 塗料一般檢驗法 (有關塗膜之物理、化學抗性之試驗法)

試驗結果:

- 請詳附件 -

---1---

本報告若有提供規範值時,該規範值僅供參考,合格之判定以委託單位實際要求為準。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. TWB 9 7

www.sgs.tw

SGS Taiwan Ltd.

t (886-4) 2359-1515

No. 9, 14th Rd. Taichung Industrial Park, Taichung 40755, Taiwan / 40755 台中市台中工業區14路9號 f (886-4) 2359-2557



Testing Laboratory 0292

材料及工程實驗室-台中

試驗報告


報告編號:TV-16-02345Z

2 OF 數:

報告日期:105年07月07日

試驗設備:

	~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~	型號
試驗級鉛筆	MITSU-BISHI	UNI



實驗室條件:

溫度:23±2℃ 濕度:50±5%

等級條件:

鉛筆硬度等級:

6B-5B-4B-3B-2B-B-HB-F-H-2H-3H-4H-5H-6H-7H-8H-9H

試驗荷重: 1000g 判定方法: 破損法

試驗結果:

試驗項目	結果
鉛筆硬度(破損法)	7H

---000---

本報告若有提供規範值時,該規範值僅供參考,合格之判定以委託單位實際要求為準。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.aspx">http://www.sgs.com/en/Terms-and-Conditions.aspx</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx">http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx</a>. Attention is thrawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not experience to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

TWB9770